

# CS 2K Clear VOC CC.19 AS

2K clear coat

## :: CHARACTERISTIC

- high initial hardness
- high UV-, chemical and mechanical resistance

## :: APPLICATION

- industrial applications
- small to medium paintwork

## :: PRODUCT DATA

### MATERIAL DATA

Colour clear coat:	Transparent
V.O.C.:	2004/42/IB(e)(840) < 840 g/l
Shelf life:	12 month in closed original container at 20°C
Density clear coat at 20°C:	0.95 - 0.97 g/cm <sup>3</sup>
Density hardener at 20°C:	0.93 - 0.95 g/cm <sup>3</sup>
Dry film thickness:	35 - 60 µm
Efficiency:	12,5 m <sup>2</sup> /l at 20µm dry film thickness



## :: HANDLING

It is strongly recommended to work with the complete system. Drying and adhesion problems cannot be excluded with use of thinning and hardening materials of external systems.

**NOTE:** Possible light colouration of the hardener doesn't affect the shade of the finishing coat.



MIXING RATIO		
	<b>2K Clear VOC CC.19 AS</b> <b>2K Hardener CC.19 AS</b> <b>Thinner</b>	<b>by volume</b>
		2 1 0 - 10% vol. on component A
	<b>2K Clear VOC CC.19 AS</b> <b>2K Hardener CC.19 AS</b> <b>Thinner</b>	<b>by weight</b>
		100 g 48 g 0 - 9% on component A
SPRAYING VISCOSITY		
	<b>DIN cup 4mm at 20°C</b>	15 - 17 seconds
APPLICATION		
	<b>Spray gun gravity feed</b>	<b>Nozzle size / pressure</b>  Nozzle size: 1.3mm Air pressure: Please pay attention to operating pressure recommendations of the manufacturer.
	<b>Application</b>	<b>spraying operations</b>  2 - 3 coats
	<b>Pot life at 20°C</b>	up to 3h
	<b>Flash off</b>	5 - 7 minutes between coats 10 minutes before baking
	<b>Dry coat thickness</b>	35 - 60 µm
	<b>Process conditions</b>	Temperature 18 - 22°C Relative air humidity 40 - 60%

PROCESSING			
	<b>Object temperature</b>	<b>20°C</b>	<b>60°C</b>
	<b>Hardener standard Full hardness</b>	6 - 7 h 5 - 7 days	25 min 25 min + 5 days/20°C
NOTE: Prior to polishing the clear coat dried at 60°C, wait up to 1h for cooling down.			
	<b>IR Drying</b>	8 - 15 min. Follow the recommendations of the IR lamp manufacturer. Keep the flash-off time before drying	

### :: STORAGE AND TRANSPORTATION CONDITIONS

Protect from freezing, heat, sunlight and moisture. Store tightly closed in a dry, cool place. Recommended storage and transportation temperature range is: +10 to +30°C. Avoid extreme temperature fluctuation.

### :: REMARKS

Allow the product to reach the recommended application temperature naturally (avoid rapid heating/cooling). It is not recommended to apply the product at a temperature below 18°C. Low application temperature changes the coating's properties and may impair the visual effect. Prior to application, the product temperature, spray booth temperature and object temperature should be adjusted to about 20°C.

## :: SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions.

In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE