

:: Faser

polyester fibreglass putty

CHARACTERISTICS

Special fibre putty

- less fibres
- more resins
- highly viscous
- easier to laminate
- easier to process
- for repairing of small rust spots
- only for use on steelbases and GRP
- Adhesion on metallic surfaces

APPLICATION

Suitable for repairing GRP, for filling very deep uneven areas and as first layer in repairing small rust spots.

PRODUCT DATA

MATERIAL DATA

- Delivery viscosity at 20°C: highly viscous
- **VOC content:** 2004/42/IIB (b) (250) < 250g/l
- Shade: brownish-transparent

HANDLING

BASE:

The base must be clean, dry and grease-free.



DOSING:

Addition of 2-3 % by weight hardener paste.

Overdosing of the hardener paste is to be avoided. Bleeding-through and colour changes in the finishing coat might be the result.

POT LIFE:

At +20°C room temperature, 4-5 minutes.

REACTION TEMPERATURE:

At least +5°C.

APPLICATION:

Spread on with a spatula

DRYING TIME:

Air drying at +20°C room temperature, 20 - 30 minutes.

SANDING CHARACTERISTICS:

Following to the given drying time.

As filling putty

First sanding - dry with P80 - P120 Re-sanding - dry with P120 - 240

REWORKING:

The fibre putty can be gone over with the following CS products: all Multi putties, all non-Multi putties, Elastic green, white or beige, Spray and Spray Plus

STORAGE:

Ca. 6 - 8 months at 18 - 20° C in closed original container



SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE