

Glas

polyester fibreglass reinforced putty

V04
05/2026

Description

- A glas fibre reinforced putty with extra long fibres

Area of application

- For filling in deep uneven areas and dents on vehicle bodywork in the area of cars, lorries, buses and railway vehicles and for repairing small rust spots.

Benefits

- Improved sanding characteristics
- Spreads more smoothly and homogeneously
- Highly concentrated filler
- Perfectly suited for GRP repairs

Product Data

Material data

Viscosity at 20°C: pasty
VOC-content: 2004/42/IIIB (b) (250) <250g/l
Colour: green

Handling

Surface:

- The base must be clean, dry and grease-free.

Mixing instructions

- Addition of 2-3 % by weight hardener paste

Pot-life:

- At +20°C room temperature, 3-4 minutes

Reaction temperature:

- At least +5°C

Application:

- Spread on with a spatula

Hardening time:

- Air drying at +20°C room temperature, 15 - 20 minutes

Sanding:

- After the specified drying time.

As filling putty

First sanding – dry with P80 - P120

Re-sanding - dry with P120 - 240

As fine putty

First sanding - dry with P120 - P180

Re-sanding - dry with P180 - P240

Reworking:

- The fine putty can be gone over with the following CS products: Elastic weiss or Elastic beige and Spray

Storage:

- ca. 6 - 8 months at 18 - 20° C in closed original container

Steel	Aluminium	Galvanized tin	GRP	Plastic	2K Polyester putty	Wood
√	X	X	√	X	√	√

Glas

polyester fibreglass reinforced putty

V04
05/2026



Storage and transportation conditions

Protect from frost, heat, sunlight and moisture. Keep the container tightly closed in a dry, cool place. Avoid extreme temperature fluctuations. Storage and transport temperature must not fall below +5°C.



Safety issues

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

© VOSSCHEMIE