

KS-300.2

Cavity Wax

V01
06/2025

Description

- Temporary corrosion protection agent for the metal industry
- Suitable for engine compartment preservation
- Light-coloured and transparent appearance
- Low viscosity adjustment

Area of application

- Specially developed for cavity preservation in motor vehicles
- Universal corrosion protection agent for machines, machine parts and tools
- Reliable protection against corrosion

Product Data

Chemical basis:	Wax-based
Colour:	Milky light / transparent
Density (15 °C) DIN 51757:	0.84 g/cm ³
Drop Point DIN 51801, Part 2:	> 100 °C
Flash Point DIN EN ISO 2719:	Approx. 70 °C
Viscosity (40 °C) DIN 53015:	36 s
Optimal Application Temperature:	20 – 30 °C
Temperature Resistance:	Up to 90 °C
Consumption:	Approx. 140 g/m ²
Drying Time:	Approx. 8 hours
Shelf Life:	Approx. 5 years in sealed original container

Handling

Surface preparation:

The surface must be clean, dry, free of grease, and rust-free. Shake or stir well before use.

KS-300.2 is delivered in liquid form. The product can be applied by spraying, brushing, dipping, or similar methods. Please note the extended drying time when used as underbody protection.

Storage Conditions:

Store in the original sealed container at a maximum of 30 °C. If stored at temperatures below 10 °C, warm up to 30 °C and homogenize before use.

KS-300.2

Cavity Wax

V01

06/2025



Notice

Allow the product to reach the recommended application temperature naturally (avoid rapid heating/cooling). It is not recommended to apply the product at temperatures below 15 °C. Low application temperatures can alter the coating properties and affect the visual result. Before use, the product temperature, spray booth temperature, and object temperature should be adjusted to approximately 20 °C.



Safety issues

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

© VOSSCHEMIE