

S.21 Spotblender

Blending paint spray

DESCRIPTION

Blending paint spray

:: AREA OF APPLICATION

 For homogeneous transition zones in the blending area of 1K and 2K clear coats as well as 2K top coats

BENEFITS

- Very good solving ability
- No spray gun application necessary

PRODUCT DATA

MATERIAL DATA

Solids by volume: 2,6%

V.O.C.: 2004/42/IIB(e)(840) < 840 g/l

Storage life: 60 months in closed original container at 20°C

:: HANDLING

We recommend polishing the surface to be treated first and then thoroughly cleaning it with silcone remover and alcohol cleaner.

Telefon: +49 (0) 4122 - 717 899 Fax: +49 (0) 4122 - 717 193 www.carsystem.org

a trademark of **VOSSCHEMIE**



V01 03/2021

MIXING RATIO		
	Shaking up	Shake until the ball becomes audible and then continue shaking for at least 3 minutes
APPLICATION		
	Application	Several thin coats
\\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\ \\	Flash off	2 - 5 minutes
	Process conditions	Temperature 18 - 25°C relative air humidity 40 - 50%
PROCESSING		
→	Empty the valve	After painting, turn the can upside down and spray the valve until empty

Telefon: +49 (0) 4122 - 717 899 Fax: +49 (0) 4122 - 717 193 www.carsystem.org



STORAGE AND TRANSPORT CONDITIONS

Protect from freezing, heat, sunlight and moisture. Store tightly closed in a dry, cool place. Recommended storage and transportation temperature range is: +18 to +25°C. Avoid extreme temperature fluctuation.

Note: The storage and transportation temperature must be not lower than +5°C. Acclimatize the product to room temperature naturally.

2004/42/IIB (e)(840) <840: The EU limit value for this product (product category: IB.e) in ready to use form is max. 840 g/litre of VOC.

:: REMARKS

Allow the product to reach the recommended application temperature naturally (avoid rapid heating/cooling). It is not recommended to apply the product at a temperature below 18°C. Low application temperature changes the coating's properties and may impair the visual effect. Prior to application, the product temperature, spray booth temperature and object temperature should be adjusted to about 20°C.

:: SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions.

In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE

Page 3 of 3

Telefon: +49 (0) 4122 - 717 899 Fax: +49 (0) 4122 - 717 193 www.carsystem.org

a trademark of **VOSSCHEMIE**