

# 2K CLEAR VOC

## CC.26 ECO-X 15/60

CC.26 ECO-X 15/60

2K CLEAR VOC

# 2K CLEAR VOC

## CC.26 ECO-X 15/60

2K KLARLACK | 2K CLEAR COAT



**CAR SYSTEM**  
EXPERIENCE.  
INNOVATION.  
QUALITY.

## CS 2K CLEAR VOC CC.26 ECO-X 15/60

Der Carsystem 2K CLEAR VOC CC.26 ECO-X 15/60 ist ein Zweikomponenten-Acryllack mit einem einfachen Mischungsverhältnis von 2 : 1 ohne Verdünner. Dieser VOC konforme Klarlack ist für die Lackierung von Einzelteilen sowie für ganze Fahrzeugpartien, wie z. B. Vorderwagen, geeignet.

- Schnelle Trocknung
- Sehr gute Verlaufseigenschaften
- Hohe Endhärte und ausgezeichnete Kratzfestigkeit
- Sehr hoher Glanzgrad
- Läuferstabil
- Anwenderfreundlich

*The Carsystem 2K CLEAR VOC CC.26 ECO-X 15/60 is a two-component acrylic clear coat with a simple 2:1 mixing ratio, requiring no thinner. This VOC-compliant clear coat is suitable for painting individual parts as well as complete vehicle sections, such as front-end assemblies.*

- Fast drying
- Excellent flow properties
- High final hardness and outstanding scratch resistance
- Very high gloss level
- Resistant to runs and sags
- User-friendly

Art.-Nr.	Beschreibung Description	KP SP	VE MOQ	EAN Code	Ursprungsland Country of origin	Zolltarifnummer Customs number
160.613	CS 2K CLEAR VOC CC.26 EcoX 15/60 A+B 1,5 l	12 St. / Box	1 Box	4102871606131	PL	39069090
160.614	CS 2K CLEAR VOC CC.26 EcoX 15/60 AK 5,0 l	4 St. / Box	1 Box	4102871606148	PL	39069090
160.615	CS 2K CLEAR VOC CC.26 EcoX 15/60 BK 2,5 l	4 St. / Box	1 Box	4102871606155	PL	39069090



**EXPERIENCE.  
INNOVATION.  
QUALITY.**

## BESCHREIBUNG

- 2K Acryl Klarlack

## TROCKNUNGSZEIT

- 15 min / 60 °C Objekttemperatur
- 3 – 4 h / 20 °C Objekttemperatur

## EINSATZGEBIET

- VOC konformer Klarlack ist für die Lackierung von Einzelteilen sowie für ganze Fahrzeugpartien, wie z.B. Vorderwagen, geeignet.

## VORTEILE

- Schnelle Trocknung
- Sehr gute Verlaufseigenschaften
- Hohe Endhärte und ausgezeichnete Kratzfestigkeit
- Sehr hoher Glanzgrad
- Läuferstabil
- Anwenderfreundlich

## ANWENDUNGSHINWEIS

Es wird dringend empfohlen im System zu arbeiten. Bei Verwendung von systemfremden Verdünnungs- und Härtermaterialien können Trocknungs- und Haftungsprobleme nicht ausgeschlossen werden.

## DESCRIPTION

- 2K acrylic lacquer

## DRYING TIME

- 15 min / 60 °C Object temperature
- 3 – 4 h / 20 °C Object temperature

## AREA OF APPLICATION

- VOC-compliant clear coat is suitable for coating individual parts as well as complete vehicle sections, such as front ends.

## BENEFITS

- Fast drying
- Excellent flow properties
- High final hardness and outstanding scratch resistance
- Very high gloss level
- Resistant to runs
- User-friendly

## APPLICATION ADVICE

It is strongly recommended to use the product within the specified system. When using thinners and hardeners from other manufacturers or non-system products, drying and adhesion problems cannot be ruled out.



**CARSYSTEM HEADQUARTERS**  
**VOSSCHEMIE GmbH**  
Esinger Steinweg 50 | 25436 Uetersen / Germany

E-Mail: [info@vosschemie.de](mailto:info@vosschemie.de)  
Tel.: +49 (0) 41 22 / 717-0 | Fax: +49 (0) 41 22 / 717-193

   [www.carsystem.org](http://www.carsystem.org)