

CS 1K NC Putty

nitrocellulose putty

03/2017

:: CHARACTERISTIC

The CS 1K NC Putty is a 1-component nitrocellulose-based filler.

:: AREA OF APPLICATION

The putty is ideal for spot repair of small unevenness's, such as scratches, holes or stone damages. By application in thin layers, the filler dries very fast and forms a smooth surface. The 1K NC Putty is applicable on polyester fillers, acrylic fillers, metal, steel, aluminium and galvanized surfaces.

:: PRODUCT DATA

MATERIAL DATA

Form:	High viscous
Colour:	Light grey
Odour:	Characteristic
Density:	1,68 g/ cm ³
VOC-content:	2004/42/IIB (b) (250) < 250g/l
Shelf-life:	12 months in unopened original container at proper storage Conditions. Store cool and dry.

:: HANDLING

SURFACE:

The surface must be cleaned, dried, degreased and matted with abrasives.

APPLICATION:

Spread on with a spatula in very thin layers and allow it to dry for 15 – 30 minutes between coats.

FILM THICKNESS:

Total film thickness should not exceed 70-80 µm.



DRYING TIME:

Air drying 30 – 50 minutes depending on the thickness at 20°C ambient temperature.

SANDING:

Following drying times given.

Hand sanding / dry P 240 – P 400

Machine sanding / dry P 240 – P 400

PROCESSING:

The CS 1K NC Putty can be worked over with the following CS products: 1K Easy Primer, 1K Easy Filler, 1K Epoxy Primer, Etch Primer, 2K VOC Filler 540, 2K Filler Vario, 2K Filler Vario Plus, 2K Filler Air Plus, 2K Filler Wet on Wet.

STORAGE:

Please note that this product contains volatile solvents. Keep tightly closed in dry, cold place. Avoid high temperature during storage and application.

:: SAFETY ISSUE

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE