

## :: Multi Light

polyester multifunctional putty

### CHARACTERISTICS

Multi Light is a next generation ultra lightweight polyester putty

- State-of-the-art filler
- Optimum sanding characteristics
- Up to 40% higher sanding removal compared with traditional putty
- Absolutely surface dry
- Adhesion to galvanised steel sheeting
- Adhesion to aluminium and steel surfaces
- Adhesion to wood
- Adhesion to polyester laminates

### APPLICATION

For filling in deep uneven areas and dents on motor vehicle bodywork in the area of cars, lorries, buses and railway vehicles.

### PRODUCT DATA

- **Delivery viscosity at 20°C:** as a paste
- **VOC content:** 2004/42/II B (b) (250) < 250g/l
- **Shade:** beige

### HANDLING

**BASE:** The base must be clean, dry and grease-free.

**DOSING:** Addition of 2-3 % by weight hardener paste.

Overdosing of the hardener paste is to be avoided. Bleeding-through and colour changes in the finishing coat might be the result.

**POT LIFE:**

**Multi Light:** At +20°C room temperature, 3-4 minutes.

**Multi Light slow:** At +20°C room temperature, 5-7 minutes.

**Multi Light super slow:** At +20°C room temperature, 12-15 minutes.

**REACTION TEMPERATURE:**

At least +5°C.

**APPLICATION:**

Spread on with a spatula

**DRYING TIME:**

Air drying at + 20°C room temperature, 20 - 30 minutes.

**SANDING CHARACTERISTICS:**

Following drying times given.

**As filling putty**

First sanding - dry with P80 - P120

Re-sanding - dry with P120 - 240

**As fine putty**

First sanding - dry with P120 - P180

Re-sanding - dry with P180 - P240

**REWORKING:**

The Multi Light putty can be worked over with the following CS products:

- Elastic weiss or Elastic beige and Spray

**STORAGE:**

Ca. 6 - 8 months at 18 - 20° C in closed original container



01/2013

## **SAFETY ISSUES**

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.

Copyright VOSSCHEMIE